

BRINGING LIFE  TO PLASTICS

MAXITHEN[®] RANGE

Colour Preparations for Margarine Cups

COLOUR PREPARATIONS FOR MARGARINE CUPS

Product MAXITHEN®			Dos	Heat Stability	Light-fastness	Food Approval GER+AT, Cd/Pb/Diarylid-free	Polymer
HP	212411	Yellow	3%	280°C	7-8	yes	HD 120 MO
HP	214061	Yellow	4%	290°C	5	yes	HD 120 MO
HP	215081	Yellow	3%	300°C	7-8	yes	HD 120 MO
HP	215121	Yellow	3%	260°C	7	yes	HD 120 MO
PP	24151	Yellow	3%	300°C	8	yes	HD 120 MO
PP	26321	Yellow	3%	300°C	4	yes	HD 120 MO
PP	210021	Yellow	3%	300°C	7	yes	HD 120 MO
PP	211051	Yellow	4%	280°C	6	yes	HD 120 MO
PP	211711	Yellow	4%	280°C	7	yes	HD 120 MO
PP	212021	Yellow	3%	260°C	7-8	yes	HD 120 MO
PP	212681	Yellow	3%	280°C	7-8	yes	HD 120 MO
PP	212691	Yellow	3%	280°C	7	yes	HD 120 MO
PP	215221	Yellow	7%	300°C	6	yes	HD 120 MO

DOS:

HEAT STABILITY:

LIGHTFASTNESS:

ALL PRODUCTS ARE:

Dosage Rate - values in %

values in °C

Woolscale 1–8; 8 = best value


Food approved in Germany/Austria

Free of pigments based on toxic heavy metals


Free of diarylid pigments

Due to low pigment concentration the values for Heat Stability and Lightfastness must be considered as guidelines only and have to be therefore tested under practical conditions.

COLOUR PREPARATIONS FOR MARGARINE CUPS



HP 212411
E=3%




HP 214061
E=4%



HP 215081
E=3%



HP 215121
E=3%



PP 24151
E=3%




PP 26321
E=3%



PP 210021
E=3%

COLOUR PREPARATIONS FOR MARGARINE CUPS




PP 211051
E=4%



PP 211711
E=4%




PP 212021
E=3%



PP 212681
E=3%



PP 212691
E=3%



PP 215221
E=7%

BUSINESS UNITS OF GABRIEL-CHEMIE GROUP:



Building & Agriculture



Home & Lifestyle



Packaging for Industrial & Consumer Goods



Cosmetics Packaging



Food & Beverage Packaging



Medical



GABRIEL-CHEMIE Gesellschaft m. b. H.

Industriestraße 1
2352 Gumpoldskirchen
Austria

Tel. +43 2252 636 30 0

Fax +43 2252 627 25 0

info@gabriel-chemie.com

WWW.GABRIEL-CHEMIE.COM